

2014



Addagrip Terraco Limited,
Bell Lane Industrial Estate,
Uckfield, East Sussex TN22 1QL
Tel: 01825 761333
Fax: 01825 768566
E-mail: sales@addagrip.co.uk

Installation Date: ____ / ____ / ____

Installer: _____

Contact: _____

Address: _____

Town: _____

County: _____

Postcode: _____

Tel: _____

Email: _____

Notes:



Tips for the maintenance of Addagrip Floor finishes

Your Addagrip floor finish should be swept or vacuumed regularly to remove dust and debris. If the floor is to be washed you should dilute a neutral detergent, by 1:40 in clean water. Liberally apply the water and detergent solution to the floor, using a slow-speed (<400rpm) scrubbing machine and white soft-medium pad or a soft-bristle brush.

Allow the detergent solution to remain on the floor for several minutes to soften deposits, do not allow the cleaner to evaporate. Care must be taken on smooth surfaces when wet as the floor maybe slippery.

Remove the detergent solution using a wet vacuum recovery floor cleaner, repeat the process with clean water before removing by wet vacuuming.

It is important that all detergent residue is removed from the surface of the floor, as detergent can become slippery affecting safety, or may remain sticky attracting and holding dirt.

Use recommended cleaning chemicals - use only recommended cleaning liquids or their equivalent in the correct concentration. Do not mix cleaning liquids, and always follow the manufacturer's instructions. Always trial on a small area first to make sure not adverse effect occurs.

Remove scuff marks regularly - to remove any rubber heel marks by abrasion use the correct machine pad, or scrub by hand, using scouring powder. For areas requiring renovation due to neglect or heavy soiling request a sample of Addagrip Terminator Floor Cleaner.

Newly laid floors must be protected from other trades during and after the initial installation, a suitable nonstaining protective covering may be required.

Newly laid floor surfaces should be kept dry and free from water spillage for a minimum of 7 days to allow the surface to fully cure.

Steam cleaners or hot pressure cleaners should NOT be used on the floor. A cold/ambient pressure washer may be used if required, but the pressure should not exceed 1400psi

Addagrip resin floor finishes are very durable and can resist many chemicals, however, some cleaning agents may shorten their service life.

Damage to floor

Should the floor area be damaged it is recommended that patch repairs are carried out as soon as possible to prevent further damage. The contractor who carried out the installation should be contacted, alternatively Addagrip can supply small repairs kits on request.

Addagrip 09/01/2014