



PU ADDASTONE PLUS RESIN BONDED POLYURETHANE

AS-PSTF + AF-SY-10

OVERVIEW

PU ADDASTONE PLUS is buff, dark grey, or light grey three-part resin surface dressing, designed to bind natural aggregates. The finish achieved provides an attractive, safe, hard wearing and low maintenance surface.

PREPARATION OF SURFACE

All bituminous surfaces to be treated with **PU ADDASTONE PLUS** must be dried for at least 7 days before using an encapsulated vacuum assisted shot blaster to remove the surface bitumen revealing the stones.

Newly installed bituminous surfaces should be installed and compacted to current British Standard specifications. Examples of various suggested build ups are available on our website.

Existing bituminous surfaces must be of sound construction; any weakness could result in a bond failure or blistering. We strongly recommend that the client should take or, instruct, that core samples are taken to confirm base suitability.

**SURFACES TO BE TREATED MUST BE DRY
DO NOT APPLY IN WET CONDITION**

MIXING & APPLICATION

PU ADDASTONE PLUS is supplied as a 3-part system; comprising of Part 'A' (Resin), Part 'B' (Hardener) and Part C (Thixotropic Agent).

1. Carefully add Part C into container 'A' and mix to a homogenous consistency. Up to 1.5% addition is the recommendation.
2. Then scrap contents of 'B' into the mixed container 'A+C' and mix thoroughly for several minutes using a low speed electric drill.

Use protective gloves and goggles. Failure to mix thoroughly will result in poor or non cured material.

The temperature of the substrate must be 3 degrees above the dew point temperature of the atmosphere. See Addagrip Dew Point table for assistance. **PU ADDASTONE PLUS** should not be applied at temperatures below 5°C nor above 30°C. Relative humidity should not exceed 80%.

Apply the mixed **PU ADDASTONE PLUS** immediately by serrated squeegee onto the prepared surface. Particular attention should be given to areas around obstructions and protrusions making sure that all surfaces are covered.

PU ADDASTONE PLUS resin bonded surfaces must be thoroughly swept/vacuumed on completion. Further sweeping/vacuuming will also be required until the initial shedding of aggregate has been exhausted. Addastone contractors will generally carry out the first main sweep/vacuum only.

Note: The colour and textures of natural aggregates may vary from batch to batch. Small particles of iron may be present in natural aggregates that could lead to possible rust spotting/staining.

PACKAGING & STORAGE

Packaged in 20kg and 1492kg units. Store containers in a clean dry area protected from direct sunlight and extreme heat and cold. Unopened containers can be stored for 6 months. Use oldest material first.

COVERAGE RATES

The minimum coverage rate for **PU ADDASTONE ASPHALT RESIN** is dependent on the chosen aggregate:

Aggregate	Resin Coverage
0.5 – 1.5mm	1.0 – 1.2kg per sqm
1.0 – 3.0mm	1.4 – 1.7kg per sqm

Quantity of aggregate required to ensure complete blanket coverage:

Aggregate	Aggregate Coverage
0.5 – 1.5mm	4.0 – 5.0kg per sqm
1.0 – 3.0mm	6.0 – 8.0kg per sqm

TECHNICAL DATA

Product	Resin bonded polyurethane
Density	1.17g/cm ³
Colour	Buff, dark grey or light grey
Application Temperature	+5°C to 30°C
Surface Temperature	Must be 3°C above the dew point temperature
Pot Life at 20°C	Approx. 30 minutes
Initial cure at 20°C	5-8 hours
Full Chemical Cure	7 days
Packaging	20kg and 1492kg resin (2.80:1 mix ratio by weight), and 10kg thixotropic units
Storage	6 months in original unopened containers

HEALTH & SAFETY

Before using this product, please ensure you have been supplied and have read carefully the following:-

1. The hazard label (complying with CLP – European Regulation (EC) No. 1272/2008 on Classification, Labelling and Packaging of substances and mixtures) applied to the container.
2. Safety Data Sheet

Avoid prolonged contact with eyes and skin. For detailed information refer to relevant safety data sheet.

CLEANING OF EQUIPMENT & SKIN

Tools, brushes etc... should be cleaned immediately after use in Addagrip Solvent Mixture. For cleaning of hands/skin, use a deep cleaning soap with water. Please note if a rash appears seek medical attention.

DISPOSAL CONSIDERATIONS

Normally the Part A resin will be mixed in its own container with Part B. When this is done correctly the resultant material in the container is inert and the label must be defaced. The container and remnant may be disposed of as normal industrial waste. Any uncured material must be disposed as hazardous waste. Please consider the regional or national regulations regarding disposal.