


Landscape House, Premier Way, Lowfields Business Park, Elland HX5 9HT Tel: 0333 000 20 50 www.marshalls.co.uk/commercial

T: 01422 312000 F: 01422 312943 E: services.advisory@marshalls.co.uk

Modal Textured 400 x 200 x 80

Date Created: 03/10/18





Natural products are manufactured from aggregates sourced locally to the works and contain no pigmentation, therefore colour variation between products from different works is possible.

The new flagship Modal range incorporates the internationally popular La Linia into a truly versatile paving collection. Available in both smooth and textured finishes, the high quality aggregates in the surface catch the light to lend a contemporary urban look to modern landscapes.

Combining any permutation of the 10 colours and 12 sizes available in the new Modal range allows for truly creative laying options. Modal is ideal for pedestrianised areas, but smaller paving units are also suitable for HGV trafficking.

DESCRIPTION		
Appearance	Two part unit with textured surface and integral spacers	
Manufacturing Process	Semi dry pressed & vibrated concrete	
Base Raw Material	Concrete	
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1339 : 2003	
CE Marking/DOP	https://www.marshalls- landscapes.co.uk/dop	
NBS Specification	Q24 10 Q24 112 Q25 120 Q25 220	Q24 110 Q24 113 Q25 125 Q25 315





OHSAS 18001 Occupatio Health and

Fair Tax











Creating Better Spaces

T: 01422 312000 F: 01422 312943 E: services.advisory@marshalls.co.uk

Modal Textured 400 x 200 x 80

PHYSICAL PROPERTIES		
Tolerances	Minimum (mm)	Maximum (mm)
Length	398	402
Width	198	202
Thickness	77	83
Work Dimensions (mm)	399 x 199 x 80	
Nominal Dimensions (mm)	400 × 200 × 80	
Tolerances on Work Dimensions (mm)	Length ±2mm, width ±2mm, thickness ±3mm	
Abrasion Resistance (mm)	≤ 23mm (Wide Wheel Abrasion Test)	
Durability (Freeze-thaw)	\leq 1.0 kg/m ² as a mean with no individual value > 1.5 kg/m ²	
Material Density	2300 kg/m³ (typically)	l.
Slip/Skid Resistance (polished)	Mean polished skid resistance value (PSRV) : > 45	
Slip/Skid Resistance (unpolished)	Mean unpolished skid resistance value (USRV) : > 45.	
Thermal Conductivity (K value)	Design data as define 2013	ed to BS EN 13369 :
Facing Layer	4mm minimum thick	ness

Av. pack size (m²)	7.2
Units Per Pack	112
Av. pack weight (kg)	1253
Packaging	All packs are shrinkwrapped onto pallets for fork off-load or crane off-load if necessary

CDECIEICATION	
SPECIFICATION	45
Approx unit weight (kg)	15
Emission of Asbestos	No content
External Fire Performance	Deemed to satisfy. See commission decision 2000/553/ECU
Reaction to fire	Class A1, see commisson decision 2000/605/EC
SITE WORKS	12 no nor m?
Coverage	13 no per m²
APPLICATION	
Suitability	For any given application, any resulting soiling (whether vehicular or pedestrian origin) will be more apparent on Light Granite than any darker shades and alternative colours, so careful consideration should be given when selecting colour in relation to application. Therefore, consideration should be given to any possible additional maintenance requirements, to ensure a desirable and acceptable appearance is provided.
Loading Classification	Category 6 - 10 large goods vehicles per week (0.15 msa)
SUSTAINABILITY	
Breeam	These units can achieve an "A" rated system when used in conjunction with the correct sub-base components

32 kg CO2 m²

Carbon Footprint

FURTHER INFORMATION

Cleaning & Maintenance	Information regarding the cleaning & maintenance of this product may be obtained on request
Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking
Weathering	It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Product Evolution	Marshalls reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice. The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details
Contact Us	For technical information on the design, specification and construction when utilising the product, contact the Technical Advisory Services Department on 0370 411 2233

