


## Coppice 240 x 160 x 80


Date Created: 05/10/18



Coppice  
Pennant Blend



Coppice  
Oak Blend



Coppice  
Cedar Blend

\*Natural products are manufactured from aggregates sourced locally to the works and contain no pigmentation, therefore colour variation between products from different works is possible.

Coppice is a cost effective, new block paving range, blended from light to dark in each of the three new colour mixes. Each single pack contains five different blends which, when laid create an impression of multiple sized block paving.

This new paving range is available in one single size; 240 x 160 x 80mm and comes in 3 versatile blends.

A Permeable priora version is also available.

### DESCRIPTION

Appearance	Solid unit with integral spacers	
Manufacturing Process	Semi dry pressed & vibrated concrete	
Base Raw Material	Concrete	
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1338 : 2003	
CE Marking/DOP	<a href="https://www.marshall's-landscapes.com/dop">https://www.marshall's-landscapes.com/dop</a>	
NBS Specification	Q24 10 Q24 112	Q24 110 Q24 113



# Coppice 240 x 160 x 80

Date Created: 05/10/18

## PHYSICAL PROPERTIES

Tolerances	Minimum (mm)	Maximum (mm)
Length	238	242
Width	158	162
Thickness	77	83
Work Dimensions (mm)	240 x 160 x 80	
Nominal Dimensions (mm)	240 x 160 x 80	
Tolerances on Work Dimensions (mm)	Length ±2mm, width ±2mm, thickness ±3mm	
Abrasion Resistance (mm)	≤ 23mm (Wide Wheel Abrasion Test)	
Durability (Freeze-thaw)	≤ 1.0 kg/m <sup>2</sup> as a mean with no individual value > 1.5 kg/m <sup>2</sup>	
Material Density	2300 kg/m <sup>3</sup> (typically)	
Slip/Skid Resistance (polished)	Mean polished skid resistance value (PSRV) : > 45	
Slip/Skid Resistance (unpolished)	Mean unpolished skid resistance value (USRV) : > 45.	
Thermal Conductivity (K value)	Design data as defined to BS EN 13369 : 2013	

## SUPPLY

Av. pack size (m <sup>2</sup> )	7.68
Av. pack weight (kg)	1430
Packaging	All packs are shrinkwrapped onto pallets for fork off-load or crane off-load if necessary

## FURTHER INFORMATION

Cleaning & Maintenance	Cleaning & maintenance details are available on request
Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking
Weathering	It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Product Evolution	Marshall's reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice. The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details
Contact Us	For technical information on the design, specification and construction when utilising the product, contact the Technical Advisory Services Department on 0370 411 2233

## SPECIFICATION

Approx unit weight (kg)	7.05
Emission of Asbestos	No content
External Fire Performance	Deemed to satisfy. See commission decision 2000/553/ECU
Reaction to fire	Class A1, see commission decision 2000/605/EC

## SITE WORKS

Coverage	27
----------	----

## APPLICATION

Loading Classification	Category 7 - 100 large goods vehicles per week
------------------------	--

## SUSTAINABILITY

Breeam	These units can achieve an "A" rated system when used in conjunction with the correct sub-base components
Carbon Footprint	32 kg CO <sub>2</sub> m <sup>2</sup>

