

Landscape House, Premier Way, Lowfields Business Park, Elland HX5 9HT Tel: 03704 11 22 33 https://www.marshalls.co.uk/commercial


T: 01422 312000 F: 01422 312943

E: services.advisory@marshalls.co.uk

Urbex Riven 450 x 450 x 50

Date Created: 07/02/19







Urbex paving provides a cost effective utility paving solution that's suitable for commercial pedestrianised areas and housebuilder pathways and patios. Available in three modular plan sizes and a choice of thicknesses, providing a paving solution that's suitable for multiple spaces.

Urbex is now available in two finishes and is a great alternative to Standard Pimple Paving. It's a particularly smart practical choice for residential areas – or for any project where spending is restricted. Available in two colour options, Buff and Natural, Marshalls' Urbex Paving means you don't have to compromise on appearance to achieve a great price – and vice versa.

DESCRIPTION	
Appearance	solid unit with riven profile
Manufacturing Process	Hydraulically pressed concrete
Base Raw Material	Concrete
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1339 : 2003
CE Marking/DOP	https://www.marshalls.co.uk/dop
NBS Specification	Q25 315



























Landscape House, Premier Way, Lowfields Business Park, Elland HX5 9HT Tel: 03704 11 22 33 https://www.marshalls.co.uk/commercial

T: 01422 312000 F: 01422 312943

E: services.advisory@marshalls.co.uk

Date Created: 07/02/19

Urbex Riven 450 x 450 x 50

DUNGS AL DE OBERTIES		
PHYSICAL PROPERTIES		
Tolerances	Minimum (mm)	Maximum (mm)
Length	448	452
Width	446	450
Thickness	47	53
Work Dimensions (mm)	448 x 448 x 50	
Nominal Dimensions (mm)	450 x 450 x 50	
Tolerances on Work Dimensions (mm)	Length ±2mm, width ±3mm	±2mm, thickness
Abrasion Resistance (mm)	≤ 23mm (Wide Whe	el Abrasion Test)
Durability (Freeze-thaw)	≤ 1.0 kg/m² as a mea value > 1.5 kg/m²	n with no individual
Material Density	2300 kg/m³ (typically)
Slip/Skid Resistance (polished)	Mean polished skid (PSRV) : > 45	resistance value
(polisifed)	(1 31(4) . > 43	
Slip/Skid Resistance (unpolished)	Mean unpolished sk (USRV) : > 45.	id resistance value

SPECIFICATION	
Approx unit weight (kg)	23
Emission of Asbestos	No content
External Fire Performance	Deemed to satisfy. See commission decision 2000/553/ECU
Reaction to fire	Class A1, see commission decision 2000/605/EC

SUSTAINABILITY	
Breeam	These units can achieve an "A" rated system when used in conjunction with the correct sub-base components
Carbon Footprint	13 kg CO2 m²

Carbon Footprint	13 kg CO2 m²
APPLICATION	
Loading Classification	Category 6 - 10 large goods vehicles per week (0.15 msa)

SITE WORKS	
Coverage	5 no per m²
SUPPLY	
Av. pack size (m²)	8.1
Units Per Pack	40
Av. pack weight (kg)	936
Packaging	All packs are suitable for crane off-load Fork lift off-load on request

7 (v. pack weight (kg)	550
Packaging	All packs are suitable for crane off-load Fork lift off-load on request
FURTHER INFORMATION	J
Cleaning & Maintenance	Cleaning & maintenance details are available on request
Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking
Weathering	It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Product Evolution	The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details. Marshalls reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice
Contact Us	For technical information on the design, specification and construction when utilising the product, contact the Technical Advisory Services Department on 0370 411 2233













BUSINESS IN THE COMMUNITY











