

# Lozenge 400 x 400 x 50

Date Created: 03/08/18



Lozenge - Buff

Created specifically to designate on-street platform edges, Marshall's Lozenge Tactile Flag Paving warns users of where Light Rapid Transport systems (LRT) and Supertram schemes' platform edges begin.

Manufactured in a pale Buff colour, the paving's slightly raised surface contrasts in tone to surrounding surfaces in order to better aid those with visual impairments. It is laid in a single strip of 400mm width with the lozenge pattern running parallel to platform edges.

Marshall's Lozenge Tactile Flag Paving should be positioned no closer than 500mm to the edge of a platform.

DESCRIPTION	
Appearance	Solid unit with profiled surface
Manufacturing Process	Hydraulically pressed concrete
Base Raw Material	Concrete
Governing Manufacturing Standards	All data where relevant manufactured, but not in compliance, to BS EN 1339 : 2003, as the tactility of paving is excluded from the Scope
CE Marking/DOP	<a href="https://www.marshall's.co.uk/dop">https://www.marshall's.co.uk/dop</a>
NBS Specification	Q25 320



# Lozenge 400 x 400 x 50

Date Created: 03/08/18

## PHYSICAL PROPERTIES

Tolerances	Minimum (mm)	Maximum (mm)
Length	396	400
Width	396	400
Thickness	47	53
Work Dimensions (mm)	398 x 398 x 50	
Nominal Dimensions (mm)	400 x 400 x 50	
Tolerances on Work Dimensions (mm)	Length ±2mm, width ±2mm, thickness ±3mm	
Abrasion Resistance (mm)	≤ 23mm (Wide Wheel Abrasion Test)	
Durability (Freeze-thaw)	≤ 1.0 kg/m <sup>2</sup> as a mean with no individual value > 1.5 kg/m <sup>2</sup>	
Material Density	2300 kg/m <sup>3</sup> (typically)	
Slip/Skid Resistance (polished)	Mean polished skid resistance value (PSRV) : > 45	
Slip/Skid Resistance (unpolished)	Mean unpolished skid resistance value (USRV) : > 45.	
Thermal Conductivity (K value)	Design data as defined to BS EN 13369 : 2013	
Transverse/FlexuralSplit/Breaking	Characteristic bending strength of 4.0 MPa with no individual result less than 3.2 MPa	

## SPECIFICATION

Approx unit weight (kg)	20
Emission of Asbestos	No content
External Fire Performance	Deemed to satisfy. See commission decision 2000/553/EU
Reaction to fire	Class A1, see commission decision 2000/605/EC

## SUSTAINABILITY

Breem	These units can achieve an "A" rated system when used in conjunction with the correct sub-base components
Carbon Footprint	13 kg CO <sub>2</sub> m <sup>2</sup>

## APPLICATION

Suitability	Laid in accordance with BS 7533-4 : 2006
-------------	--

## SITE WORKS

Coverage	6.25 no per m <sup>2</sup>
----------	----------------------------

## SUPPLY

Av. pack size (m <sup>2</sup> )	5.8
Units Per Pack	36
Av. pack weight (kg)	720
Packaging	All packs are suitable for crane off-load. Fork lift off-load on request

## FURTHER INFORMATION

<b>Cleaning &amp; Maintenance</b>	Information regarding the cleaning & maintenance of this product may be obtained on request
<b>Efflorescence</b>	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking
<b>Weathering</b>	It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
<b>Product Evolution</b>	The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details. Marshalls reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice

<b>Contact Us</b>	For technical information on the design, specification and construction when utilising the product, contact the Technical Advisory Services Department on 0370 411 2233
-------------------	---

