

255 x 205 x 600 Conservation Kerb

Date Created: 17/04/18



Tetured Silver Grey 5953

Tetured Charcoal 5951

Tetured Harvest Buff 5952

For a striking and modern kerb system, the Conservation Kerb offers a slightly wider profile than a standard kerb, aiding modern design aesthetics in any application.

It's a high-strength kerb, precision manufactured before going through a secondary shot texturing process. This gives it the appearance of exposed granite aggregate, a look that's available in three colours: Harvest Buff, Charcoal and Silver Grey. It also contains up to 48.3% recycled materials in its manufacturing.

Different sizes and variants of this durable kerb are available. The 145x255mm and 255x205mm versions both have a wide selection including internal radius, external radius, straights, left and right hand drop kerbs and more. Download the brochure to see the full range.

- Smart and contemporary look
- Exposed granite aggregate appearance
- 145x255mm and 255x205mm versions
- Choice of 3 colours

DESCRIPTION

Appearance	Solid unit with textured surface	
Manufacturing Process	Hydraulically pressed concrete	
Base Raw Material	Concrete	
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1340 : 2003	
CE Marking/DOP	https://www.marshall's.co.uk/dop	
NBS Specification	Q10 112	Q10 10
	Q10 510	



255 x 205 x 600 Conservation Kerb

Date Created: 17/04/18

- Utilises up to 48.3% recycled materials

PHYSICAL PROPERTIES

Tolerances on Work Dimensions (mm)	Length ± 3 mm, width ± 3 mm, thickness ± 3 mm
Abrasion Resistance (mm)	≤ 23 mm (Wide Wheel Abrasion Test)
Durability (Freeze-thaw)	≤ 1.0 kg/m ² as a mean with no individual value > 1.5 kg/m ²
Material Density	2300 kg/m ³ (typically)
Slip/Skid Resistance (polished)	Mean polished skid resistance value (PSRV) : > 45
Slip/Skid Resistance (unpolished)	Mean unpolished skid resistance value (USRV) : > 45 .
Thermal Conductivity (K value)	N A
Transverse/FlexuralSplit/Breaking	Characteristic bending strength of 3.5 MPa with no individual result less than 2.8 MPa

SPECIFICATION

Approx unit weight (kg)	62
Emission of Asbestos	No content
External Fire Performance	Deemed to satisfy. See commission decision 2000/553/ECU
Reaction to fire	Class A1, see commission decision 2000/605/EC

DESIGN GUIDANCE

Technical information	Refer to Marshall's online paving design tool www.marshall's.co.uk/commercial/toolbox/paving-design
-----------------------	--

APPLICATION

Suitability	Laid in accordance with BS 7533-6 : 1999
-------------	--

FURTHER INFORMATION

Cleaning & Maintenance	Information regarding the cleaning & maintenance of this product may be obtained on request
Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking
Weathering	It should be appreciated that with all products weathering and site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Product Evolution	The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details. Marshall's reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice
Contact Us	For technical information on the design, specification and construction when utilising the product, contact the Technical Advisory Services Department on 0370 411 2233

