

Stonespar - Grishma Blend

Date Created: 26/07/19



Stonespar -
Grishma Blend

*It should be noted that colour variations and markings are characteristic of Natural Stone. Inherent variations cannot be controlled nor the precise shade of stone guaranteed.

Marshall's Stonespar range is a strong and durable sandstone plank paving collection featuring pre-designed colour blends inspired by the four seasons.

The Stonespar Grishma Blend contains a mix of complementary beige and buff hues to create a unique patterned aesthetic. The paving stones come pre-mixed in the crate to ensure speedy installation and reduce space on site.

Stonespar paving is suitable for urban areas such as town centres and commercial spaces.

Their non-slip properties make them ideal for pedestrianised areas while they can also withstand occasional traffic, such as in spaces where delivery and emergency vehicles require access.

Marshall's also offers the chance to blend these stones to your own unique blend so please contact us for further details.

DESCRIPTION

Appearance	Blend so refer to individual stone data sheets
Manufacturing Process	Sawn
Geological Type	Cambrian Sandstone
Quarry of Origin	Kota Region, Rajasthan, India
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2012
Petrographical Description	50% Brackendale, 25% Brownridge, 25% Laurel Bank
CE Marking/DOP	https://www.marshalls.co.uk/dop



Stonespar - Grishma Blend

Date Created: 26/07/19

PHYSICAL PROPERTIES

Work Dimensions (mm)	600 x 130 x 65
Tolerances on Work Dimensions (mm)	Class 1 tolerances to all dimensions as standard
Abrasion Resistance (mm)	18mm (Mean value to EN 14157 : 2004 (Hev = 18.1mm))
Durability (Freeze-thaw)	Varies
Material Density	2534 kg/m ³ (Mean value to EN 1936 : 2006)
Open Porosity (%)	3% (Mean value to EN 1936 : 2006)
Compressive Strength (MPa)	238 MPa (Mean value to EN 1926 : 2006 (Lev = 195 MPa))
Water Absorption (%)	1 % (Mean value to EN 13755 : 2008 (Hev = 1.39%))
Transverse/FlexuralSplit/Breaking	34 MPa (Mean value to EN 12372 : 2006 (Lev = 26.69 MPa))

TEXTURE SPECIFIC PROPERTIES

	Blasted
Surface Roughness (Rz-µm)	53
Slip Resistance (BS 14231) (Dry)	97
Slip Resistance (BS 14231) (Wet)	71

MANUFACTURING

Materials Control CE Marked to BS EN 1341 Paving

SUSTAINABILITY

ERI Score Our Score: 3.6
Cluster Score: 2.4

Carbon Footprint 131.95 kg CO₂ m²

FURTHER INFORMATION


Contact Us For technical information on the design, specification and construction when utilising the product, contact the Technical Advisory Services Department on 0370 411 2233



Stonespar - Grishma Blend

Date Created: 26/07/19

Suggested Plan Sizes



600 x 130

The plan sizes shown above illustrate popular sizes of our Natural Stone. Bespoke sizes are available upon request.

