



KÖSTER Polysil TG 500

Deeply penetrating primer for damp and salt burdened substrates, immobilizes salts, consolidates sanding substrates

Features

KÖSTER Polysil TG 500 is a thin fluid product based on a polymers and silicates. On salt burdened and on damp substrates it leads to a reduction of the pore volume and decreases the likelihood of new salt efflorescence development. It also increases the chemical and mechanical resistance of mineral building materials. Depending on the substrate, the product penetrates the surface up to 2 cm deep. KÖSTER Polysil TG 500 also has strengthening and hydrophobing properties. The material is compatible with mortars, plasters, cementitious slurries, and concrete.

Technical Data

Application temperature	min. + 5 °C
Specific gravity	1.03 g/cm ³
Surface	transparent, slightly sticky

Application of next layer:

- after 30 minutes - cementitious building materials
- after min 24 hours - acrylate and silicate paints

Fields of Application

KÖSTER Polysil TG 500 is used to consolidate, strengthen, and to protect mineral substrates and to reduce their absorbency, even of such problematic building materials as sandstone. KÖSTER Polysil TG 500 decreases the danger of new salt efflorescence development and raises the resistance of mineral substrates to the freeze thaw cycle. All mineral substrates are suited for application except for gypsum. KÖSTER Polysil TG 500 can be used as primer beneath polymer-modified bitumen thick film sealants such as KÖSTER Deuxan 2C and KÖSTER Bikuthan 2C.

Substrate

KÖSTER Polysil TG 500 can be applied to weakly and to strongly absorbant, to dry and to moist substrates. The substrate has to be free of oil and loose particles. Salt efflorescence must be removed by brushing prior to application of KÖSTER Polysil TG 500.

Application

Deeply penetrating priming:

KÖSTER Polysil TG 500 can be brush or spray applied. During the curing time, the surrounding and substrate temperature must not fall below 0 °C. Salts which came through the surface of the substrate during the curing process must be removed by brushing. After full cure, salts will be immobilized in the substrate.

Internal waterproofing using rigid sealing slurries:

In order to install extremely resistant coatings using KÖSTER NB 1 Grey, the substrate is first primed with KÖSTER Polysil TG 500 a minimum of 30 minutes before the application of KÖSTER NB 1 Grey, (without addition of KÖSTER SB-Bonding Emulsion). The second layer of KÖSTER NB 1 Grey can be applied after the first coat has set.

Surface protection:

KÖSTER Polysil TG 500 is sprayed, rolled, or brushed onto the substrate To strengthen and improve the chemical and mechanical resistance of mineral building materials, (Consumption approx. 130 – 250 g/m²). The protective coating reaches its final cure after approximately 16 hours.

Consumption

Approx. 0.1 - 0.25 kg/m² depending on substrate, strongly absorbent substrates may require more.

On strongly absorbent substrates the consumption may be higher.

Cleaning

Clean tools immediately after use with water.

Packaging

M 111 001	1 kg bottle
M 111 010	10 kg jerrycan

Storage

Store the material cool but frost-free. In originally sealed containers it can be stored for a minimum of 12 months.

Safety

Wear protective gloves and goggles during application. Observe all governmental, state, and local safety regulations when processing the material.

Related products

KÖSTER Adhesive Mortar	Prod. code B 530 033
KÖSTER Repair Mortar NC	Prod. code C 535 025
KÖSTER Hydrosilicate Adhesive	Prod. code M 170 020
SK	
KÖSTER Restoration Plaster	1 Prod. code M 661 025
Grey	
KÖSTER Restoration Plaster	2 Prod. code M 662 025
White	
KÖSTER Restoration Plaster	2 Prod. code M 663 030
Fast	
KÖSTER Restoration Plaster	2 Prod. code M 664 025
Light	
KÖSTER Restoration Plaster	2 Prod. code M 665 025
Fast	
KÖSTER Restoration Plaster	E Prod. code M 668
Grey	
KÖSTER Hydrosilicate Board	Prod. code M 670
KÖSTER MF 1	Prod. code P 280
KÖSTER Elastic Roof	Prod. code R 238 015
KÖSTER Dachflex	Prod. code R 260 020
KÖSTER NB 1 Grey	Prod. code W 221 025
KÖSTER NB 2 White	Prod. code W 222 025
KÖSTER NB 1 Fast	Prod. code W 223 025

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

KÖSTER Restoration Slurry	Prod. code W 225 025
KÖSTER NB Elastic Grey	Prod. code W 233 033
KÖSTER NB Elastic White	Prod. code W 234 033
KÖSTER NB 4000	Prod. code W 236 020
KÖSTER Bikuthan 2C	Prod. code W 250 028
KÖSTER Deuxan 2C	Prod. code W 252 032

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

Delta Membrane Systems Ltd, Delta House, Merlin Way, North Weald, Epping, Essex CM16 6HR
Tel:01992 523 523. Email: info@deltamembranes.com . Website: www.deltamembranes.com