

waves

by Roger Albero



Petra 1

TECHNICAL CHARACTERISTIC

Manufactured product technical features are validated by officially approved laboratory tests.

- **Freeze resistance** 25 cycles of ice (-25°C) / defrosting (+15°C) without fissures, layers nor scaling having occurred.
- **Flexural and compressive strength** (UNE EN 1015-11 (196-1):
Flexural: 78 kgf/cm² (average value among the different standard colours)
Compressive: 440 Kp/cm² (average value among the different standard colours)

- Colours**
- > Standard colours [without coloured pigments] grey [1] | white [2] | ochre [3]
 - > Other colours (with coloured pigments) on order. Percentage increase according the colour characteristics and the order request.

- Finished**
- Scoured.
 - Anti-graffiti superficial treatment optional.
 - Water repellents treatment superficial optional.

Manufactured in Architectural Cement

Es un banco, es una jardinera, es un banco-jardinera. Para sentarse junto a la naturaleza.

És un banc, és una jardinera, és un banc-jardinera. Per seure a vora la natura.


It's a bench. It's a planter. It's a bench-planter. To sit down next to nature.

Est un banc, est une jardinière, est un banc-jardinière. Pour s'asseoir dans la nature.


È una banco, è una fioriera, è un banco-fioriera. Per sedere assieme alla natura.

Eine Sitzbank, ein Blumenkasten, im Endeffekt ein Blumenkasten mit Sitzgelegenheit. Zum Ausruhen in der Natur.

waves B | 840 kg



waves R 300 | 910 kg



waves J (planter) | 640 kg | 295 L

