

roxane

by Ton Riera



Peta 1

TECHNICAL CHARACTERISTIC

Manufactured product technical features are validated by officially approved laboratory tests.

• Freeze resistance 25 cycles of ice (-25°C) / defrosting (+15°C) without fissures, layers nor scaling having occurred.

• Flexural and compressive strength (UNE EN 1015-11 (196-1)):

Flexural: 78 kgf/cm² (average value among the different standard colours)


Compressive: 440 Kgf/cm² (average value among the different standard colours)

Colours
 > Standard colours [without coloured pigments]
 grey [1] | white [2] | ochre [3]
 > Other colours (with coloured pigments) on order.
 Percentage increase according the colour characteristics and the order request.


Finished
 Scoured.
 Anti-graffiti superficial treatment optional.
 Water repellents treatment superficial optional.

Manufactured in Architectural Cement


roxane | 340 kg



roxane valla



roxane bike



Uno de nuestros elementos más versátiles, delimita y ordena de diferentes modos y para diferentes usos el espacio.

Un dels nostres elements més versàtils, delimita i ordena de diferents maneres i per a diferents usos l'espai.

One of our most versatile elements, it restricts and organises space in different ways for different uses.

Un des articles les plus polyvalents, défini et rangée de différentes façons toute type d'espaces.

Uno dei nostri elementi più versatili, definisce e ordina lo spazio in modi diversi e per diversi usi.

Eines unserer vielseitigsten Elemente, das verschiedenartige Abgrenzungen und Anordnungen des Raumes für unterschiedliche Nutzungen ermöglicht.

