

# K-FLEX® ST DUCT



TECHNICAL DATA			
Property	Value		Test method
Temperature range	From -40 °C to +85 °C		EN 14706 EN 14707
Thermal conductivity $\lambda$ W/(m•K)	Thicknesses $\leq$ 25mm	Thicknesses $>$ 25mm	EN 13787 EN 12667
	-20 °C = 0,031 0 °C = 0,033 +20 °C = 0,035 +40 °C = 0,037	-20 °C = 0,034 0 °C = 0,036 +20 °C = 0,038 +40 °C = 0,040	
Corrosion prevention	pH neutral (7 $\pm$ 0,5)		EN 13468
Permeability $\mu$	$\geq$ 7000		EN 12086
Fire rating	Euroclass B-s3, d0		EN 13501-1
Ecological data	Without CFCs and HCFCs		

K-FLEX® reserves the right to change data and technical requirements without notice.

RANGE		
	Thicknesses	Height
K-FLEX® ST DUCT - Sheets	6-8-10-12-15-20-30 mm	1500 mm

